

UNCLASSIFIED

AD

419078

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

419078 (21) Abstract for American Physical Society, Washington Meeting, April 25-27, 1957.

(6) Ferroelectric Behavior of $\text{NH}_4\text{Fe}(\text{SO}_4)_2 \cdot 12\text{H}_2\text{O}$. * (10) F. Jona, K. Vedam, T. Mitsui and R. Pepinsky, The Pennsylvania State University.

FILE COPY
A dielectric anomaly occurs in ammonium iron alum at low temperatures¹. A re-investigation of this crystal has been carried out.

The dielectric constant is about 6 at room temperature, and rises to a sharp peak, of approximately 60, at -185°C . A large ac field applied along the cubic [100] direction causes the appearance of double hysteresis loops above and close to the transition point, indicative of a first-order ferroelectric transition, as observed in the case of BaTiO_3 ². In a 60 cps

electric field of 20 KV/cm, the double loops can be observed within a range of about 2°C above the transition temperature. Ferroelectric loops appear at and below the Curie point, but can only be observed in a temperature range 1 to 2° below the transition. The spontaneous polarization P_s is of the order of 0.3 microcoulomb/cm², and the coercive field about 20 KV/cm. At about 2° below the Curie point, the hysteresis loop collapses suddenly to a narrow ellipse. This indicates that the motion of the domain walls is hindered and the coercive field is far larger than the breakdown field.

The behavior of the crystal under a strong ac field applied along the cubic [111] direction is interesting. In this case the crystal acts if the transition were of the second order.

*Supported by Signal Corps Engineering Laboratories and Air Force Office of Scientific Research.

¹R. Guillien, Compt. Rend. 209, 21 (1939).

²W. J. Merz, Phys. Rev. 91, 513 (1953).

#1.10

RECEIVED
15 JAN 1958
AFOSR